

# Method card

BUZIL-WERK Wagner GmbH & Co. KG

## CORRIDOR® COMPLETE S 732

**Application area:**  
Floor / coating



pH 8.5

<p><b>Dilution</b></p>	<p>pure</p>		
<p><b>Suitable for</b></p>	<p>Public institutions, offices; Public educational institutions</p>	<p><b>Not suitable for</b></p>	<p>Public institutions, offices; Public educational institutions</p>
<p><b>Application</b></p>	<p>Water-resistant floor coverings; Linoleum; PVC; Rubber; Natural or artificial stone; Sealed parquet and cork</p>		
<p> <b>Trouble Shooting</b></p> <p>Before initial use: Test material compatibility!</p>	<p><b>Issue / Failure / Requirement</b></p> <ul style="list-style-type: none"> <li>▪ Poor penetration / shine</li> <li>▪ Foaming with „craters“ as a result after drying</li> <li>▪ Powdering off when used</li> <li>▪ Severe marking when used</li> <li>▪ Grey / mat appearance of surface due to hard water</li> <li>▪ Damage on surface (discoloration, material swelling, etc.)</li> </ul>	<p><b>Solving Issue</b></p> <ul style="list-style-type: none"> <li>▪ Covering too porous, apply pore filler / another layer</li> <li>▪ Covering too rough, spread more slowly when applying</li> <li>▪ Before applying, do not let the covering dry / deep clean again</li> <li>▪ Intensive cleaning with Maradin HC 43, Aktiv G 433, spray cleaning with Corridor® Spray S 770</li> <li>▪ Clean periodically with O Tens Azid G 501</li> <li>▪ Check material's chemical and water resistance</li> </ul>	

# Method card

BUZIL-WERK Wagner GmbH & Co. KG

## ALTERNATIVE PRODUCT | CORRIDOR® COMPLETE S 732

Application area:  
Floor / coating



pH 8.5

Alternative Product	Differentiation	Application
<b>Planta® Multi Gloss P 320</b>	Free of metallic salts	Glossy floor coating
<b>Corridor® Glorin S 734</b>	Free of metallic salts	Glossy floor coating
<b>Corridor® Jewel S 741</b>	Suitable for sports flooring (DIN 18032/2)	High-gloss floor coating
<b>Corridor® Matt S 737</b>	High-performance dispersion, free of metallic salts	Silk matt floor coating